

BARACADE SILANE 100

HIGH PERFORMANCE WATER REPELLENT

DESCRIPTION

BARACADE SILANE 100 is a breathable, ready-to-use, colorless, non-yellowing, deep penetrating concrete and masonry water repellent. BARACADE SILANE 100 is a 100% silane formulation that produces a hydrophobic treatment to reduce water absorption. BARACADE SILANE 100 protects concrete, block, stone and brick against the damaging effects of water intrusion, deicing chemicals, freeze-thaw exposure and airborne contaminants such as acid rain, smog and industrial fumes. Due to the 100% silane composition, BARACADE SILANE 100 exhibits low volatility and higher coverage rates than solvent based silane materials.

PRIMARY APPLICATIONS

- Sidewalks
- Ramps
- Parking decks
- Bridge decks

FEATURES/BENEFITS

- Reduces water absorption
- Protects against air-borne contaminants, such as acid rain
- Protects concrete against the damaging effects of water intrusion and deicing chemicals

TECHNICAL INFORMATION

Material Properties @ 75° F (24°C)

Flash point min	145°F (63°C)
Silane %.....	100
Weight/gal	7.6 lbs/gal
VOC content.....	248 g/L
Resistance to UV	excellent
Abrasion resistance	excellent
Average depth of penetration	0.2 in (5 mm)

NCHRP 244, Series II Reduction of water absorption, %

Days in water	
1 day.....	94
3 days.....	89

Chloride penetration

% Reduction	91
-------------------	----

PACKAGING

BARACADE SILANE 100 is packaged in 5 gal (18.9 L) pails and 55 gal (208 L) drums.

SHELF LIFE

2 years in original, unopened package.

COVERAGE

Surface Type	ft ² /gal (m ² /L) per coat
Smooth Concrete	200 to 350 (4.91 to 8.59)
Exposed Aggregate	225 to 375 (5.52 to 9.20)
Decks/Ramps	200 to 300 (4.91 to 7.36)

Because of variations in surface density, the following coverage rates are approximate and are intended for estimating purposes only. Use test applications on actual surfaces to accurately determine coverage rates. Extremely porous surfaces may require two coats of BARACADE SILANE 100.

DIRECTIONS FOR USE

Surface Preparation: Cure new concrete 28 days before application. Surface must be clean, dry, open capillary, structurally sound, free of curing or form release compounds and other contaminants that will prevent the proper penetration of product. Prior to application, joints and moving cracks must be properly sealed with an elastomeric joint sealant. Non-moving cracks and voids wider than 1/64 inch (0.4 mm) must be filled with a suitable patching material. Do not apply product to a wet surface. Surfaces must dry a minimum of 24 hours following rain or exposure to other sources of moisture. Install caulking before product application. Mask or protect adjacent surfaces, including grass, plants, shrubs, glass, autos, and asphalt from overspray or drips. For surfaces that have had prior coatings or treatments, contact your local Euclid Chemical representative for recommendations.



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



Application: Use low pressure airless spray equipment with solvent resistant hose and gaskets. Garden type sprayers may be appropriate for smaller projects. Brushes and rollers on large projects may not achieve a uniform coverage rate. Apply BARCADE SILANE 100 in a single application to the horizontal surface with enough material to saturate the surface. Remove excess material with a broom or squeegee. If a second coat is required it should be applied “wet on wet” before first coat dries.

Typical traffic-ready time for BARCADE SILANE 100 is 4 hours after application at 75°F (24 °C) and 50% relative humidity. Cooler temperatures and/or high humidity will extend the dry time.

CLEAN-UP

Clean tools and equipment with alcohol, mineral spirits or similar solvent immediately following use. Clean drips and over spray while still wet. Clean glass and other non absorbent materials soon after application.

PRECAUTIONS/LIMITATIONS

- Store at temperatures below 90°F (32 °C).
- BARCADE SILANE 100 is a DOT combustible liquid. Avoid fire, open flame and sparks.
- Do not dilute.
- Do not allow to puddle. All product should penetrate the substrate with no surface build-up.
- Do not apply to a frost filled surface or when the temperature is below 32°F (0 °C).
- Do not apply if rain is expected within 12 hours.
- Not intended for use on below grade applications or applications where hydrostatic pressures exist. May not be effective on certain types of limestone or marble. Test application is always recommended to confirm performance and appearance. Use in a well ventilated area.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 6.11

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.